






Quantitative results



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :

O SiO2 1-Jun-1999 12:00 AM

Comment:

Na Albite 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Si SiO₂ 1-Jun-1999 12:00 AM

Cl KCl 1-Jun-1999 12:00 AM

K MAD-10 Feldspar 1-Jun-1999 12:00 AM

Ca Wollastonite 1-Jun-1999 12:00 AM




As InAs 1-Jun-1999 12:00 AM

Hg HgTe 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	48.73	74.16
Na K	6.63	7.03
Al K	1.17	1.05
Si K	1.26	1.09
Cl K	9.47	6.50
K K	6.67	4.15
Ca K	2.98	1.81
As L	6.88	2.24
Hg M	16.21	1.97
Totals	100.00	



Quantitative results



Spectrum processing :

Peak possibly omitted : 9.700 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :

O SiO2 1-Jun-1999 12:00 AM

Comment:

Na Albite 1-Jun-1999 12:00 AM

Si SiO2 1-Jun-1999 12:00 AM

S FeS2 1-Jun-1999 12:00 AM

Cl KCl 1-Jun-1999 12:00 AM

K MAD-10 Feldspar 1-Jun-1999 12:00 AM

Ca Wollastonite 1-Jun-1999 12:00 AM

As InAs 1-Jun-1999 12:00 AM

Nb Nb 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	46.04	69.80
Na K	5.33	5.63
Si K	1.22	1.05
S K	6.83	5.16
Cl K	8.78	6.01
K K	6.93	4.30
Ca K	2.41	1.46
As L	11.53	3.73
Nb L	10.93	2.85
Totals	100.00	